

Technical data sheet

Media Type: PP 500 S

Description: Scrim-supported needle punched felt

Composition: 100% polypropylene

SAMPLES
AVAILABLE
ON REQUEST

Weight		500 +/- 10	gr/m ²
Thickness		1.8-2.0	mm under 20 gr/cm ² pressure
Airpermeability		8.4-10.8	m ³ /m ² /min @ 12.7 mm W.G
Max breaking strength	down	80-120	kg/5cm width
	cross	120-160	kg/5cm width
Max elongation	down	65-95	% at break (KSK 0521)
	cross	55-75	% at break (KSK 0521)
Bursting strength		40-50	kg/cm ²
Finish			heat set & singed one side